

## Sandell's Step Flashing

### SECTION 1

#### MATERIAL IDENTIFICATION INFORMATION

Mineral Spirits

Copper (Insert Solid)

Cotton Fabric (Insert Solid)

Granite Grit (Insert Solid)

ACGH TLV 500PPM

Note: None of the information listed on this MSDS should apply to application or use in the finished state. Only under the most adverse conditions during the manufacturing state is this data applicable.

### SECTION 2

#### PHYSICAL/CHEMICAL CHARACTERISTICS

Boiling Point: 315°F (157°C)

Specific Gravity (H2O=1): 1.1

Vapor Pressure: 68°F (20°C)

Melting Point: N/A

Vapor Density: 3.9

Evaporation Rate: 0.1

Solubility in Water: None

Appearance and Odor: Brown to black solid with faint petroleum odor.

### SECTION 3

#### FIRE AND EXPLOSION HAZARD DATA

Flash Point: Over 400°F (204°C)

Flammability Limits in Air Volume: 1.0–7.0

Extinguisher Media: Foam, CO2, or Dry

Chemical

Special Fire Fighting Procedures: Do not use water.

### SECTION 4

#### REACTIVITY HAZARD DATA

Stability: Stable

Conditions to Avoid: None (Non-Reactive)

Hazardous Polymerization: Conditions to avoid—poor ventilation can cause excessive inhalation of solvent vapors.

### SECTION 5

#### HEALTH HAZARD DATA

Sign and Symptoms of Exposure: Inhalation of solvent in poorly ventilated area may cause dizziness.

Medical Conditions Generally Aggravated by

Exposure: Excessive skin contact can lead to dry irritated skin.

Emergency First Aid Procedures: Seek medical assistance for further treatment, observation

### SECTION 6

#### CONTROL AND PROTECTIVE MEASURES

Respiratory Protection: Area should be well ventilated.

Protective Gloves: Normal work gloves

Eye Protection: Safety glasses or goggles

Ventilation to be Used: Local exhaust

Other Protective Clothing and Equipment: None

### SECTION 7

#### PRECAUTIONS FOR SAFE HANDLING AND USE/LEAK PRODECURES

Steps to be Taken if Material is Spilled or

Released: Area should be well-ventilated, respirators can be used.

Precautions to be Taken in Handling and

Storage: Do not store above 120°F (49°C).

Other Precautions and/or Special Hazards: None

#### TECHNICAL ASSISTANCE:

Call Sandell directly for technical assistance or product questions:

New York: 800.283.3888

Alabama: 877.726-3355

Wisconsin: 800.323-3565



[www.sandellmfg.com](http://www.sandellmfg.com)



**SANDELL**  
Corporate Office  
310 Wayto Road  
Schenectady NY 12303  
Toll Free: 1-800-283-3888  
Fax: 1-518-357-9636

**HOHMANN & BARNARD**  
Corporate Headquarters  
30 Rasons Court  
Hauppauge, NY 11788  
Toll Free: 1-800-645-0616  
Fax: 1-631-234-0683

**MARYLAND**  
Hohmann & Barnard  
7079-A Oakland Mills Rd  
Columbia, MD 21046  
Toll Free: 1-800-999-7816  
Fax: 1-410-290-9316

**ILLINOIS**  
Hohmann & Barnard -  
6100 S. New England Ave  
Chicago, IL 60638  
Toll Free: 1-800-323-7170  
Fax: 1-773-586-6710

**CANADA:** Blok-Lok  
12 Ashbridge Circle  
Woodbridge, ON,  
L4L 3R5, Canada  
Toll Free: 1-800-561-3026  
Fax: 1-905-266-2272

**PENNSYLVANIA**  
Foamtastic Products  
441 Boot Road, Suite 100  
Downingtown, PA 19335  
Toll Free: 1-800-645-0616  
Fax: 1-631-234-0683

**TEXAS**  
Hohmann & Barnard  
2415 Cold Spring Road  
Ft. Worth, TX 76106  
Toll Free: 1-800-822-5228  
Fax: 1-817-626-3819

**ALABAMA**  
Hohmann & Barnard-  
1902 Woodlands Industrial Dr.  
Trussville, AL 35173  
Toll Free: 1-800-296-0771  
Fax: 1-205-956-5292